

DULUX AcraTex 951 Trowel On 2mm

PRODUCT CODE 194-20822

Data Sheet No. AUDA0456

APPROVALS APAS-0118/4 (system approval)

Description

DULUX AcraTex 951 Trowel On 2mm texture coating is a range of granular, water-based, high build acrylic texture coatings for application by trowel to various masonry substrates.

Features

7 year warranty
Water based
Fast processing
Long "wet edge"

Benefits

Guaranteed long term exterior durability.
Easy, safe and economical clean-up.
Range of texture profiles possible.
Quick, efficient trowel application with long workability.

Uses

DULUX AcraTex 951 Trowel On 1.5mm textured coatings are designed to give a durable highly decorative trowel applied finish for inter/exterior for use on surfaces that may have surface imperfections. DULUX AcraTex Trowel On 951 1.5mm is a low profile granular texture coating on smooth substrates.

Performance Guide

Weather	Excellent resistance to cracking, flaking and chalking as part of a full system.	Salt	Resists salt spray.
Heat	Up to 90C (dry)	Water	Water Vapour Transmission 56.5g/24hr/sq.m. Water Transmission 220g/24hr/sq.m/kPa.
Solvent	Resists alcohol and aliphatic hydrocarbons. Sensitive to other strong solvents.	Abrasion	Good resistance to abrasion especially when topcoated with DULUX AcraTex 955 AcraShield.
Acid	Slight softening with dilute acids. Best when topcoated with DULUX AcraTex 955 AcraShield.	Alkali	Slight softening with dilute alkalis. Best when topcoated with DULUX AcraTex 955 AcraShield.

Data Sheet	DULUX AcraTex 951 Trowel On 2mm		
DuSpec Data Code	AUDA0456	Page No	1 of 3
Issue No	8.0	Date Issued	14/12/2011


DULUX AcraTex 951 Trowel On 2mm

Data Sheet No. AUDA0456

Typical Properties and Application Data

Gloss Level	Matt	Thinner	Not recommended
Gloss Level Ind		Spread Rate	0.7 sqm/L
Volume Solids	75.0	Components	1
Colour	White & can be tinted to a colour range or factory tinted to order. 1Y per litre maximum tint.	Toxicity	Lead free. Dry film is non-toxic and conforms to AS1647, Part 3.
Number of Coats	One	Shelf life	12 months maximum
V.O.C Level	< 47 g/L untinted	Wet film per coat	Recommended 1533 µm
Touch Dry	60 Minutes	Dry film per coat	Recommended 1150 µm
Clean Up	Clean all equipment with water.	Recoat	24 Hours

Application Method



Application Guide

Surface Preparation

Ensure alkaline surfaces have aged for 30 days minimum.
 All surfaces must be cured, clean, sound and free of all contaminants such as form oils, release agents and mortar splashes. Surface imperfections, misalignments and protrusions must be levelled and patched and completely flush to surrounding surfaces. Metal, tie wire, etc. on surface must be removed or treated against corrosion.
 Prime substrate with DULUX AcraTex 501 AcraPrime. Ensure that it is cured completely and covers the substrate evenly.

Application Procedure and Equipment

Product should be thoroughly mixed before use.
 Refer to the DULUX AcraTex Application Manual for detailed application instructions.
 2mm Grade: Steel trowel/polystyrene float at 0.71 sq.m/l finished with a polystyrene float.
 Trowel and Hawk finished with a polystyrene float.

Health and Safety

MSDS Number	14557335	Using Safety Precautions	Wear eye protection
Health Effects	For detailed information refer to product label and the current Material Safety Data Sheet available through Dulux Sales and Customer Service Offices 132377 AUS. Health Effects: Splashes to the eye may cause eye irritation.	Protective Equipment	0
Storage	0		

In the case of emergency please call 1800 033 111

Data Sheet	DULUX AcraTex 951 Trowel On 2mm		
DuSpec Data Code	AUDA0456	Page No	2 of 3
Issue No	8.0	Date Issued	14/12/2011

Dulux**DuSpec****DATA SHEET****Dulux AcraTex****DULUX AcraTex 951 Trowel On 2mm****Data Sheet No. AUDA0456****Precautions and Limitations**

A DULUX warranty will be provided confirming protection against flaking & peeling for a period of seven years when the full DULUX AcraTex system is applied by a Dulux AcraTex trained applicator, according to specification, & at the specified spreading rates, & to the surface preparation details described in the DULUX AcraTex Specification Manual.

DULUX AcraTex 951 Trowel On 2mm must only be applied in air temperatures between 10C and 30C and must be protected from rain and frost for the first 24 hours. Avoid application in full sun or hot, windy conditions.

Transport and Storage

Pack A	194-20822	Flash point	NA
Sizes	15 Litre	UN Number	NA
Weight	30Kg	Package Group	NA
Dangerous Goods Class	NA		
Shipment Name	Not dangerous goods.; No special transport requirements.		

Disclaimer

Dulux and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating systems.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (Australia) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "AcraTex" and Other marks followed by ® are registered trademarks of DuluxGroup (Australia) Pty Ltd ABN 67 000 049 427. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton, Victoria 3168 AU ABN 67 000 049 427

Data Sheet	DULUX AcraTex 951 Trowel On 2mm		
DuSpec Data Code	AUDA0456	Page No	3 of 3
Issue No	8.0	Date Issued	14/12/2011