

DULUX AcraTex 958 AcraSand

PRODUCT CODE 194-51943

Data Sheet No. AUDA0470

APPROVALS

Description

DULUX AcraTex 958 AcraSand is an extremely tough 100% pure acrylic high build coating, especially formulated to produce a granular, near flat, appearance very much like that of fine granular sandstone in two coats.

Features

Water based
Easy to texture
Versatile application
7 year warranty

Benefits

Easy, safe and economical clean-up.
Range of texture profiles possible.
Quick, efficient application with roller and brush.
Guaranteed long term exterior durability.


Uses

DULUX AcraTex 958 AcraSand can be used where extreme high performance is required and where a more natural granular appearance is aesthetically desired. Its high build rheology will cover small holes and fine hairline cracks in a single fast applying / economical coat on all masonry substrates.

Performance Guide

Weather	Excellent resistance to cracking, flaking and chalking as part of full system.	Salt	Resists salt spray especially when topcoated with DULUX AcraTex 955 AcraShield.
Heat	Up to 90C (dry).	Water	NA
Solvent	Resists alcohol and aliphatic hydrocarbons. Sensitive to strong solvents.	Abrasion	Good abrasion resistance especially when topcoated with DULUX AcraTex 955 AcraShield.

Typical Properties and Application Data

Gloss Level	Flat	Thinner	Not recommended.
Gloss Level Ind		Spread Rate	4.0 sqm/L
Volume Solids	50.0	Components	1
Colour	White and a range of DULUX colours. 1Y per litre maximum tint.	Toxicity	Lead free. Dry film is non-toxic and conforms to AS1647, Part 3.
Number of Coats	Two	Shelf life	24 months maximum
V.O.C Level	< 75 g/L untinted	Wet film per coat	Recommended 250 µm
Touch Dry	45 minutes	Dry film per coat	Recommended 125 µm
Clean Up	Clean all equipment in water.	Recoat	2 hours

Application Method


DULUX AcraTex 958 AcraSand

Data Sheet No.	AUDA0470
-----------------------	-----------------

Application Guide

Surface Preparation

All surfaces must be cured, clean, sound and free of all contaminants such as forms oils, release agents & mortar splashes. Surface imperfections misalignments & protrusions must be levelled, patched & completely flush to surrounding surfaces. Metal, tie wire etc on surface must be removed or treated against corrosion. Prime substrate with DULUX AcraTex 501 AcraPrime. Ensure that it is cured completely and covers the substrate evenly.

Application Procedure and Equipment

Refer to the DULUX AcraTex Application Manual for detailed instructions. Product should be thoroughly mixed before use. Application is by brush or nap roller . A minimum of two coats are required (minimum DFT of 125 micrometres) to avoid "holidays" in the coating.

Brush and nap roller.

Health and Safety

MSDS Number	14557369	Using Safety Precautions	Wear eye protection
Health Effects	For detailed information refer to current Material Safety Data Sheet available through Dulux Sales and Customer Service Offices 132377 AUS. Health Effects: Splashes to the eye may cause eye irritation.	Storage	0

In the case of emergency please call 1800 033 111

Precautions and Limitations

A DULUX warranty will be provided confirming protection against flaking & peeling for a period of seven years when the full DULUX AcraTex system is applied by a DULUX AcraTex trained applicator, according to specification, & at the specified spreading rates, & to the surface preparation details described in the AcraTex Specification Manual. DULUX AcraTex 958 AcraSand must only be applied in air temperatures between 10C and 30C and must be protected from rain and frost for the first 24 hours. Avoid application in full sun or hot, windy conditions.

Transport and Storage

Pack A	194-51943	Flash point	NA
Sizes	15 litre	UN Number	NA
Weight	23 kg	Package Group	NA
Dangerous Goods Class	NA		
Shipment Name	Not dangerous goods. No special transport requirements.		

Data Sheet	DULUX AcraTex 958 AcraSand		
DuSpec Data Code	AUDA0470	Page No	2 of 3
Issue No	12.0	Date Issued	14/12/2011



DATA SHEET



DULUX AcraTex 958 AcraSand

Data Sheet No. AUDA0470

Disclaimer

Dulux and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating systems.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (Australia) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "AcraTex" and Other marks followed by ® are registered trademarks of DuluxGroup (Australia) Pty Ltd ABN 67 000 049 427. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton, Victoria 3168 AU ABN 67 000 049 427

Data Sheet	DULUX AcraTex 958 AcraSand		
DuSpec Data Code	AUDA0470	Page No	3 of 3
Issue No	12.0	Date Issued	14/12/2011