

DULUX AcraTex SEDONA

PRODUCT CODE 19485911-12

Data Sheet No. AUDA1394

APPROVALS AS4548.4 : Long Life Coatings for Masonry

Description

DULUX AcraTex SEDONA is a high solids, flexible, roller applied coating that provides a decoative sandy texture.

Conforms to Australian Standard AS4548 Long Life Coatings for Masonry, Category 4

Features

High Solids - High Film build
Flexibility
Water Resistant
Pastel and Ultra Deep Bases
Various Finish options
Self Priming

Benefits

Enhances Sponge Finish Render profile
Increased system Crack Bridging performance
Good External Durability - Weather resistance.
Wide colour range, tintable for fast project turn-around
Light relief Sandy Texture (nap roller) or Medium Texture (texture roller)
No primer required on sound, cured masonry substrates

Uses

DULUX AcraTex SEDONA has been developed for use as a mid build, water repellent masonry coating to provide an even light sandy texture (applied by conventional nap roller) to sponge finished cement rendered walls.

The sandy profile and higher film build of AcraTex SEDONA enhances a typical sponge finish cement render profile providing greater consistency of texture and increased crack bridging capability compared to conventional low build paint systems.

Performance Guide

Weather	Excellent resistance to cracking, flaking and chalking.	Salt	Resists salt spray.
Heat	Up to 90C (dry).	Water	Low water transmission - Weather resistant
Solvent	Resists alcohol and aliphatic hydrocarbons. Sensitive to other strong solvents.	Abrasion	Good resistance to abrasion.
Acid	Slightly softening with dilute acids.	Alkali	New Cement / Concrete surfaces should be allowed to cure for 28 days to stabilise alkalinity

Data Sheet	DULUX AcraTex SEDONA		
DuSpec Data Code	AUDA1394	Page No	1 of 3
Issue No	6.0	Date Issued	14/12/2011

DULUX AcraTex SEDONA

Data Sheet No. AUDA1394

Typical Properties and Application Data

Gloss Level	Matt	Thinner	Not recommended
Gloss Level Ind		Spread Rate	3.0 sqm/L
Volume Solids	48.0	Components	1
Colour	Pastel base and Ultra Deep Base allowing for most Dulux Colour Specifier. (Max. 3Y/L tinter)	Toxicity	Lead free. Dry film is non-toxic and conforms to AS1647, Part 3.
Number of Coats	2	Shelf life	24 months maximum
V.O.C Level	< 75 g/L untinted	Wet film per coat	Recommended 333 µm
Touch Dry	60 Minutes	Dry film per coat	Recommended 160 µm
Clean Up	Clean all equipment with water.	Recoat	2 Hours

Application Method

Application Guide

Surface Preparation

All surfaces must be cured, clean, sound and free of all contaminants such as form oils, release agents and mortar splashes. Masonry substrates (including cement render) should be cured for 28 days before coating. Surface imperfections, misalignments and protrusions must be levelled and patched flush to surrounding surfaces. Metal, tie wire, etc. on surface must be removed or treated against corrosion.

If substrate is powdery or friable prime with Dulux AcraTex AcraPrime. (refer AcraPrime data sheet for detail)
Where Patching is required, patch with DULUX AcraTex 500 AcraPatch (after priming), and spot prime patching using DULUX AcraTex 501/1 AcraPrime. (refer AcraPatch Data Sheets for detail)

Application Procedure and Equipment

Product should be thoroughly mixed before use.
Refer to the DULUX AcraTex Application Manual for detailed application instructions.

NAP ROLLER finish (Light relief Sandy Texture)
Apply multiple coats using a 10 - 20mm Nap roller at 3-4 sq.m / litre
2 coats minimum recommended

LOW PROFILE TEXTURE (Medium Texture profile) :
Apply 1 coat with a low profile black Texture Roller at 2 -3 sq.m / litre
Apply a 2nd (finishing coat) with a nap roller at 3-4 sq.m / litre

Notes

When cutting in edges , brush and roll-in a continuous process to avoid differences in gloss level.
Application on single areas should be completed uninterrupted.
All independent tests are available on request.

Data Sheet	DULUX AcraTex SEDONA		
DuSpec Data Code	AUDA1394	Page No	2 of 3
Issue No	6.0	Date Issued	14/12/2011

DULUX AcraTex SEDONA

Data Sheet No.	AUDA1394
-----------------------	-----------------

Health and Safety

MSDS Number	21666	Using Safety Precautions	Wear eye protection and when spraying wear a dust mask
Health Effects	For detailed information refer to product label and the current Material Safety Data sheet available through Dulux Sales and Customer Service Offices 132377 AUS. Health Effects: Splashes to the eye may cause eye irritation.	Flammability	Non Flammable
Personal	When spraying, inhalation of mists may produce respiratory irritation.		

In the case of emergency please call 1800 033 111

Precautions and Limitations

A DULUX warranty will be provided confirming protection against flaking & peeling for a period of 5 years when the full AcraTex system is applied by a DULUX AcraTex trained applicator, according to specification, & at the specified spreading rates, & to the surface preparation details described in the DULUX AcraTex Specification Manual. DULUX AcraTex SEDONA must only be applied in air temperature between 10C and 30C and must be protected from rain and frost for the first 24 hours. Avoid application in full sun or hot, windy conditions.

Transport and Storage

Pack A	19485911-12	Flash point	NA
Sizes	15 Litre	UN Number	NA
Weight	22 Kg	Package Group	NA
Dangerous Goods Class	NA		
Shipment Name	Not dangerous goods.; No special transport requirements.		

Disclaimer

Dulux and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating systems.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (Australia) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "AcraTex" and Other marks followed by ® are registered trademarks of DuluxGroup (Australia) Pty Ltd ABN 67 000 049 427. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton, Victoria 3168 AU ABN 67 000 049 427

Data Sheet	DULUX AcraTex SEDONA		
DuSpec Data Code	AUDA1394	Page No	3 of 3
Issue No	6.0	Date Issued	14/12/2011