

Dulux Professional Exterior Acrylic Gloss

AUDD0142

Part A	662 LINE
Approvals	APAS 0280/1 (White, Deep & Ultra Deep Base)

Description

DULUX PROFESSIONAL Exterior Gloss Acrylic is a durable, exterior 100% acrylic gloss with good wet edge for lapping, minimum roller spatter and roller fly-off and excellent hold up on high spots.

Features

- Water based
- 100% Acrylic Latex
- Good wet edge
- Good body

Benefits

- Same day recoat and easy clean up.
- Long term durability - lasts longer, colours do not fade.
- Quick to use, frequent lapping is not necessary.
- Minimum spatter or roller fly-off; less splashes.

Uses






Use DULUX PROFESSIONAL Exterior Gloss Acrylic as a long-lasting exterior gloss finish on all classes of masonry, bricks, concrete, render, fibro cement etc. and all suitably primed timber and metals.

Precautions And Limitations

All preparation and painting must conform to AS2311: The Painting of Buildings.
Do not apply to roofs or surfaces used for the collection of drinking water. Do not paint at temperatures below 10C or when the temperature of surface may fall below 10C during the drying period.
Check the adhesion of old paint by cutting an 'X' through the film with a razor blade or trimming knife, press cellulose tape firmly across the cut and rip it off. If the old paint comes off with the tape it should be removed before repainting.
Occasionally when dew or condensation forms on the newly dried film, a slight milky deposit will be observed on the film. This is quite normal and does not result in reduced performance simply hose or wipe it with a damp rag and it will not reappear.

Performance Guide

Weather	Very good resistance to weathering, with very low level of chalking, colour change & dirt pick-up.	Salt	NA
Heat Resistance	Up to 70C. May soften at elevated temperatures and pick up dirt.	Water	Resists prolonged rain and condensation.
Solvent	Sensitive to aromatic hydrocarbons, alcohols and ketones.	Abrasion	Moderate resistance to abrasion.
Acid	NA	Alkali	NA

Typical Properties																											
Gloss Level	55-70 at 60 degrees	Thinner	Water																								
Colour	Can be machine tinted to a comprehensive pastel and medium dark colour range.	Components	1																								
Toxicity	Lead free. Dry film is non-toxic and conforms to AS1647, Part 3.	V.O.C. Level	< 55g/L (average)																								
Touch Dry	30 Minutes																										
Clean Up	 Water																										
Clean Up Description	Thoroughly clean all equipment in water after use.																										
Application Method	    Air Spray Airless Spray Brush Roller																										
Application Conditions	<table border="0" style="width: 100%;"> <tr> <td style="text-align: center;">Solids By Volume</td> <td style="text-align: center;">39.4</td> <td></td> <td></td> </tr> <tr> <td></td> <td style="text-align: center;">Min</td> <td style="text-align: center;">Max</td> <td style="text-align: center;">Recommended</td> </tr> <tr> <td>Wet Film Per Coat (microns)</td> <td style="text-align: center;">63</td> <td style="text-align: center;">63</td> <td style="text-align: center;">63</td> </tr> <tr> <td>Dry Film Per Coat (microns)</td> <td style="text-align: center;">25</td> <td style="text-align: center;">25</td> <td style="text-align: center;">25</td> </tr> <tr> <td>Recoat Time (min)</td> <td style="text-align: center;">2 Hours</td> <td style="text-align: center;">Indefinite</td> <td></td> </tr> <tr> <td>Theoretical Spread Rate (m²/L)</td> <td style="text-align: center;">16</td> <td style="text-align: center;">16</td> <td style="text-align: center;">16</td> </tr> </table>			Solids By Volume	39.4				Min	Max	Recommended	Wet Film Per Coat (microns)	63	63	63	Dry Film Per Coat (microns)	25	25	25	Recoat Time (min)	2 Hours	Indefinite		Theoretical Spread Rate (m²/L)	16	16	16
Solids By Volume	39.4																										
	Min	Max	Recommended																								
Wet Film Per Coat (microns)	63	63	63																								
Dry Film Per Coat (microns)	25	25	25																								
Recoat Time (min)	2 Hours	Indefinite																									
Theoretical Spread Rate (m²/L)	16	16	16																								

Application Guide	
Surface Preparation	<ul style="list-style-type: none"> All surfaces must be thoroughly cleaned and free of all dirt, dust, grease, loose or flaking paint. Efflorescence or mould on masonry or concrete surfaces must be treated, then apply primer, sealer or undercoat as required.
Application Procedure And Equipment	<ul style="list-style-type: none"> Brush, roller, conventional or airless spray Stir contents thoroughly before and during use with a broad flat stirrer, using an upward lifting action. Brush/Roller: Rinse brush or roller in water before starting and use while still slightly damp. Apply two full even coats direct from the container. Under hot or windy conditions or on very absorbent surfaces, up to 100 ml clean water may be added per litre to assist application. Use a short nap roller. Avoid excessive brushing or rolling back into paint which has been drying some minutes. Airless/Conventional Spray: Suitable for application by all standard spray equipment. If necessary thin with up to 100 ml per litre of water to aid atomisation.

Health And Safety			
MSDS Number	45450, 0	Health Effects	For detailed information refer to the product label and the current Material Safety Data Sheet available through Customer Service. Health Effects: Splashes to the eye may cause eye irritation. When spraying, inhalation of mists may produce respiratory irritation. For detailed information refer to the product label and the current Material Safety Data Sheet available through Customer Service. Health Effects: Splashes to the eye may cause eye irritation. When spraying, inhalation of mists may produce respiratory irritation.
Protective Equipment	Personal Protective Equipment: Wear eye protection and when spraying wear a dust mask.		
In the case of emergency, please call 1800 033 111			

Transport And Storage			
Pack A	662 LINE	Shipment Name	Not dangerous goods. No special transport requirements.
Size 4 Litre 10 Litre 15 Litre		Weight 5.1 Kg 13.1 Kg 20.4 Kg	
Flash Point	NA	UN Number	NA
Dangerous Goods Class	NA	Package Group	NA

Disclaimer

Dulux, Selleys and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating/product systems.
 DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (Australia) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating/product systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Selleys" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "Acratex" and Other marks followed by ® are registered trademarks of DuluxGroup (Australia) Pty Ltd ABN 67 000 049 427. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton, Victoria 3168 AU ABN 67 000 049 427