

DULUX PROFESSIONAL Int / Ext Semi Gloss Acrylic

PRODUCT CODE 665 LINE

Data Sheet No. AUDD0143

APPROVALS GPC-L-27; APAS-0260/2, AS3730, Part 2 & 9.

Description

DULUX PROFESSIONAL Interior Semi Gloss Acrylic is a high quality, scrubbable semi gloss 100% acrylic paint for interior/exterior use, with excellent flow and lapping properties.

Features

Water based
 Hard wearing/scrubbable
 Interior & Exterior
 Good application properties

Benefits

Same day recoat, easy clean up and low odour
 One product can be used in a large number of areas
 Convenient - no need to use two different products
 Minimum roller spatter, good levelling

Uses

DULUX PROFESSIONAL Interior Semi Gloss Acrylic is a high quality hard wearing scrubbable semi gloss wall and ceiling finish for kitchens, bathrooms, laundries, rumpus rooms, in schools, hospitals etc., and for all suitably prepared exterior surfaces.

Performance Guide

| | | | |
|----------------|--|-----------------|--|
| Weather | Excellent resistance to weathering. | Salt | NA |
| Heat | Up to 70C. May soften at elevated temperature and suffer dirt pick up. | Water | Resists prolonged rain and condensation. |
| Solvent | Sensitive to aromatic hydrocarbons, alcohols and ketones. | Abrasion | Resists light abrasion. |
| Acid | NA | Alkali | NA |

Typical Properties and Application Data

| | | | |
|------------------------|---|--------------------------|--|
| Gloss Level | 20-30 at 60 degrees | Thinner | Water |
| Gloss Level Ind | | Spread Rate | 16.1 sqm/L |
| Volume Solids | 37.0 | Components | 1 |
| Colour | Can be machine tinted to a comprehensive pastel and medium dark colour range. | Toxicity | Lead free. Dry film is non-toxic and conforms to AS1647, Part 3. |
| V.O.C Level | < 55g/L untinted | Wet film per coat | Recommended 62 µm |
| Touch Dry | 30 Minutes | Dry film per coat | Recommended 23 µm |
| Clean Up | Thoroughly wash brushes in water before re-using. | Recoat | 2 Hours |


Application Method


DULUX PROFESSIONAL Int / Ext Semi Gloss Acrylic

Data Sheet No. AUDD0143

Application Guide

Surface Preparation

All surfaces must be thoroughly cleaned and free of all loose dirt, dust, grease, loose or flaking paint. Efflorescence or mould on masonry or concrete surfaces must be treated. Flatten gloss surfaces by thorough sanding and wipe clean with a damp cloth, then apply primer, sealer or undercoat as required.

Application Procedure and Equipment

Stir contents thoroughly before and during use with a broad flat stirrer, using an upward lifting action.

Brush/Roller: Apply two full even coats direct from the container. Under hot or windy conditions or on very absorbent surfaces, up to 100 ml clean water may be added per litre to assist application. Use a short nap roller. Avoid excessive brushing or rolling back into paint which has been drying some minutes.

Airless/Conventional Spray: Suitable for application by all standard spray equipment. If necessary thin with up to 100 ml per litre of water to aid atomisation.

Brush, roller, conventional or airless spray.

Health and Safety

MSDS Number 45509

Health Effects For detailed information refer to the product label and the current Material Safety Data Sheet available through Customer Service.
Health Effects: Splashes to the eye may cause eye irritation. When spraying, inhalation of mists may produce respiratory irritation.
Personal Protective Equipment: Wear eye protection and when spraying wear a dust mask.

Protective Equipment Personal Protective Equipment: Wear eye protection and when spraying wear a dust mask.

In the case of emergency please call 1800 033 111

Precautions and Limitations

All preparation and painting must conform to AS2311: The Painting of Buildings.

Avoid exposure to steam and condensation for 48 hours after application.

Seven days are required after application to develop maximum hardness and stain removal properties. Most stains and scuff marks can be removed with a sponge wet with detergent solution. Do not use abrasive cleaners.

Do not apply at temperatures below 10C or when the temperature of surface may fall below 10C during the drying period.

Occasionally under steamy conditions an uneven appearance may develop early in the life of the coating. This is easily removed with a damp sponge.

Transport and Storage

Pack A 665 LINE

Sizes 4 Litre 10 Litre 15 Litre

Weight 5.7 Kg 13.9 Kg 20.5 Kg

Dangerous Goods Class NA

Shipment Name Not dangerous goods. No special transport requirements.

Flash point NA

UN Number NA

Package Group NA

| | | | |
|-------------------------|---|--------------------|------------|
| Data Sheet | DULUX PROFESSIONAL Int / Ext Semi Gloss Acrylic | | |
| DuSpec Data Code | AUDD0143 | Page No | 2 of 3 |
| Issue No | 11.0 | Date Issued | 14/12/2011 |



DATA SHEET



| | |
|--|--------------------------------|
| DULUX PROFESSIONAL Int / Ext Semi Gloss Acrylic | |
| | Data Sheet No. AUDD0143 |

Disclaimer

Dulux and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating systems.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (Australia) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "Acratex" and Other marks followed by ® are registered trademarks of DuluxGroup (Australia) Pty Ltd ABN 67 000 049 427. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton, Victoria 3168 AU ABN 67 000 049 427

| | | | |
|-------------------------|---|--------------------|------------|
| Data Sheet | DULUX PROFESSIONAL Int / Ext Semi Gloss Acrylic | | |
| DuSpec Data Code | AUDD0143 | Page No | 3 of 3 |
| Issue No | 11.0 | Date Issued | 14/12/2011 |