

**Dulux Texture Full Cover**

**AUDD1229**

<b>Part A</b>	195-85684
<b>Approvals</b>	NA

**Description**  
 DULUX Full Cover Texture is a high build texture finish formulated to provide full coverage of brick mortar joints and surface imperfections.

- Features**
- Water based
  - High build 100% Acrylic paint
  - Easy application
  - Full cover over brick mortar joints



- Benefits**
- Same day recoat and clean up
  - Proven durability at high film builds
  - Achieves texture finish without special training
  - Low cost alternative to traditional rendering methods

**Uses**  
 DULUX Full Cover Texture is a 100% acrylic texture ideal for application over brick but also suitable over concrete, fibre cement and masonry. Specially designed for a DIY consumer to transform brick walls with an even render finish.

**Precautions And Limitations**  
 All preparation and painting must conform to AS2311: The Painting of Buildings. Do not apply at temperatures below 10C or when the temperature may fall below 10C during the drying period. In summer, paint on the shady side of the building. Do not apply during hot and windy conditions. Protect from rain for 24 hours after application.

**Performance Guide**

<b>Weather</b>	Excellent resistance to weathering with minimal colour change and dirt pick up.	<b>Heat Resistance</b>	Softens and suffers from dirt pick up over 70 degrees.
<b>Water</b>	Resists prolonged rain and condensation.	<b>Solvent</b>	Sensitive to aromatic hydrocarbons and alcohols.
<b>Abrasion</b>	Good resistance to abrasion.		

Typical Properties																											
<b>Gloss Level</b>	0-5 at 60 degrees	<b>Thinner</b>	Water																								
<b>Colour</b>	Can be tinted to a wide range of pastel and medium depth colours.	<b>Components</b>	1																								
<b>Toxicity</b>	Lead free. Dry film is non-toxic.	<b>V.O.C. Level</b>	< 10g/L untinted																								
<b>Touch Dry</b>	1 hour																										
<b>Clean Up</b>	 Water																										
<b>Clean Up Description</b>	Clean all equipment with water																										
<b>Application Method</b>	 Roller																										
<b>Application Conditions</b>	<table border="0"> <tr> <td style="text-align: right;"><b>Solids By Volume</b></td> <td style="text-align: center;">54</td> <td></td> <td></td> </tr> <tr> <td></td> <td style="text-align: center;"><b>Min</b></td> <td style="text-align: center;"><b>Max</b></td> <td style="text-align: center;"><b>Recommended</b></td> </tr> <tr> <td style="text-align: right;"><b>Wet Film Per Coat (microns)</b></td> <td style="text-align: center;">1019</td> <td style="text-align: center;">1019</td> <td style="text-align: center;">1019</td> </tr> <tr> <td style="text-align: right;"><b>Dry Film Per Coat (microns)</b></td> <td style="text-align: center;">550</td> <td style="text-align: center;">550</td> <td style="text-align: center;">550</td> </tr> <tr> <td style="text-align: right;"><b>Recoat Time (min)</b></td> <td style="text-align: center;">4 Hours</td> <td style="text-align: center;">Indefinite</td> <td></td> </tr> <tr> <td style="text-align: right;"><b>Theoretical Spread Rate (m<sup>2</sup>/L)</b></td> <td style="text-align: center;">1</td> <td style="text-align: center;">1</td> <td style="text-align: center;">1</td> </tr> </table>			<b>Solids By Volume</b>	54				<b>Min</b>	<b>Max</b>	<b>Recommended</b>	<b>Wet Film Per Coat (microns)</b>	1019	1019	1019	<b>Dry Film Per Coat (microns)</b>	550	550	550	<b>Recoat Time (min)</b>	4 Hours	Indefinite		<b>Theoretical Spread Rate (m<sup>2</sup>/L)</b>	1	1	1
<b>Solids By Volume</b>	54																										
	<b>Min</b>	<b>Max</b>	<b>Recommended</b>																								
<b>Wet Film Per Coat (microns)</b>	1019	1019	1019																								
<b>Dry Film Per Coat (microns)</b>	550	550	550																								
<b>Recoat Time (min)</b>	4 Hours	Indefinite																									
<b>Theoretical Spread Rate (m<sup>2</sup>/L)</b>	1	1	1																								

Application Guide	
<b>Surface Preparation</b>	<ul style="list-style-type: none"> <li>All surfaces must be thoroughly cleaned and free of all dirt, loose and flaking paint. Efflorescence or mould must be treated before application of paint. New concrete, mortar or cement render must be allowed to cure for 4 to 8 weeks depending on concrete thickness and drying conditions.</li> <li>Block down unpainted brick and concrete surfaces using a brick or masonry rubbing stone to remove high spots and loose sand, then broom down.</li> <li>To test the adhesion of previously painted surfaces, cut an 'X' through the existing paint with a sharp blade, press cellulose tape firmly across the cut and then rip the tape off. If the old paint or render comes off, it should be removed.</li> <li>On porous surfaces, applying a priming coat of Dulux Texture Primer will condition the surface and help aid application of the Full Cover product.</li> <li>NOTE - Medium Texture can also be used as a priming coat.</li> </ul>
<b>Application Procedure And Equipment</b>	<ul style="list-style-type: none"> <li>Dulux Full Cover Texture Roller and float</li> <li>Stir contents thoroughly before and during use with a broad flat paddle, using an up and down scooping action. Pour the material from the 10L product pail into a 15L Application pail - this will act as a roller tray does for normal paint.</li> <li>Application is in 2 parts: Delivery (via the Dulux Full Cover Roller) and Finishing (using a plastic float)</li> </ul> <p>DELIVERY: generously load the roller directly from the 15L application pail and apply with a smooth, steady action from the ground upwards in vertical strips of 1/2 to 3/4 metre lengths. Reload the roller after each strip and repeat until 4 to 5 strips are applied. Do not overspread the product. Even out material by rolling diagonally across the surface. It is important to work swiftly to allow time for the finishing process and this can be best achieved by working in a team, with one "delivering" and the other "finishing".</p> <p>LEVELLING: holding the plastic float at an angle of approx. 45 degrees, with the leading edge angled up, and working from the ground up, push the material across the surface to fill joints and low spots. This should level out the texture before it sets.</p> <p>FINISHING: After cleaning the plastic float, finish the levelled area in circular strokes to further fill and level out the area. Work in larger, lighter strokes as the material levels out.</p> <p>Lubricate the float intermittently by cleaning with a wet sponge.</p> <p>Repeat the above delivery and finishing procedure, maintaining a working wet edge, until completed.</p> <p>2 coats are recommended but additional coats may be required depending upon the depth of the mortar joints.</p> <p>Remove any masking tape before the coating has dried.</p> <ul style="list-style-type: none"> <li>The weight of a 10L pail of Full Cover Texture is approximately 17.5kg (about the same weight as a 15L can of paint).</li> <li>Tinter can be dispersed using a shaker machine, but a gyroscopic shaker machine (15L or above) is required.</li> <li>Please note: a piston (up/down) shaker will not disperse tinter into the product effectively.</li> </ul> <p>Where a suitable shaker machine does not exist, hand mixing using a "masher" or using an electric drill mixer should be used. Hand mixing using a "masher" will take between 2-3 minutes per pail. Retailers who are hand mixing will require an empty pail of water for cleaning the masher behind the counter.</p>

Health And Safety			
<b>MSDS Number</b>	20461, 0	<b>Health Effects</b>	For detailed information refer to the product label and the current Material Safety Data Sheet available through Dulux Customer Service. Health Effects: Splashes to the eye may cause eye irritation For detailed information refer to the product label and the current Material Safety Data Sheet available through Dulux Customer Service. Health Effects: Splashes to the eye may cause eye irritation
<b>Protective Equipment</b>	Wear eye protection.		
<b>In the case of emergency, please call 1800 033 111</b>			

Transport And Storage			
<b>Pack A</b>	195-85684	<b>Shipment Name</b>	Not dangerous goods.; No special transport requirements.
<b>Size</b>	10 litre	<b>Weight</b>	17.5 Kg
<b>Flash Point</b>	NA	<b>UN Number</b>	NA
<b>Dangerous Goods Class</b>	NA	<b>Package Group</b>	NA

**Disclaimer**

Dulux, Selleys and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating/product systems.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (Australia) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating/product systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Selleys" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "Acratex" and Other marks followed by ® are registered trademarks of DuluxGroup (Australia) Pty Ltd ABN 67 000 049 427. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton, Victoria 3168 AU ABN 67 000 049 427