

## Dulux Zincanode 402 Zinc Primer

AUDI0539

<b>Specifications</b>	Approved to APAS 2916, AS/NZS 3750-9 Type 2.
-----------------------	--

<b>Description</b>
Two pack zinc rich epoxy primer

<b>Features And Benefits</b>	
<ul style="list-style-type: none"> <li>Overcoat with epoxies, polyurethane and chlor rubbers without special techniques</li> <li>Economical and user friendly epoxy zinc coating</li> <li>Provides excellent corrosion protection</li> </ul>	<ul style="list-style-type: none"> <li>Rapid dry and overcoat times</li> <li>Suitable for use in environments up to 200°C</li> </ul>

<b>Uses</b>
<p>ZINCANODE 402 is a two-pack epoxy zinc rich primer designed to provide exceptional corrosion resistance in harsh exposures by sacrificial methods. ZINCANODE 402 is recommended for use over abrasive blast cleaned steel surfaces in most harsh environments, especially where overcoating is required without special mist or seal coat techniques.</p> <p>ZINCANODE 402 offers ease of application, high film builds without mud-cracking and exceptional adhesion to field weld areas cleaned by power sanding or power wire brushing. It is specified for use in power generation plants, bulk handling equipment and oil refineries. Also in mining and chemical processes, offshore structures and exposed pipelines.</p>

<b>Performance Guide</b>			
<b>Weatherability</b>	Epoxy coatings may yellow with time. On exterior exposure some chalking may also occur. This will not detract from the protective properties of the coating. Use a weatherable topcoat if required for appearance.	<b>Salts</b>	Excellent resistance to neutral and alkali salts when suitably topcoated.
<b>Heat Resistance</b>	Up to 200°C dry heat.	<b>Water</b>	Suitable for immersion in fresh and salt water when suitably topcoated.
<b>Solvents</b>	Resists splash and spillage of aromatic hydrocarbon solvents and most common alcohols.	<b>Abrasion</b>	Very good when fully cured.
<b>Acids</b>	Not recommended for acid conditions.	<b>Alkalis</b>	Do not use in strongly alkaline conditions unless suitably topcoated.

Typical Properties			
<b>Classification</b>	Zinc Rich Epoxy Primer	<b>Finish</b>	Matt
<b>Colour</b>	Grey Green	<b>Components</b>	2
<b>Flash Point</b>	Base 32°C, Hardener 25°C	<b>Pot Life</b>	8 Hours (25°C)
<b>Shelf Life</b>	12 months minimum @ 25°C	<b>Mixing Ratio (V/V)</b>	Part A : 4 Part B : 1
<b>Thinner</b>	DULUX Epoxy Thinner (920-08925)	<b>Suitable Substrates</b>	Abrasive blast cleaned steel
<b>Line/Shade</b>	<ul style="list-style-type: none"> <li>730-81386 Part A</li> <li>976-63033 Hardener</li> </ul>	<b>Topcoats</b>	Single and two pack Dulux products
<b>Product Code</b>	PC 122		
<b>Meets GBCA VOC Requirement?</b>	N/A		
<b>Application Methods</b>	<b>Other:</b> Conventional, airless spray or air assisted spray. Brush and roller for small areas.		
<b>Application Conditions</b>		<b>Min</b>	<b>Max</b>
	<b>Air Temperature</b>	10	45
	<b>Substrate Surface Temperature</b>	10	45
	<b>Relative Humidity</b>	0	85
<b>Solids By Volume</b>	48		
	<b>Min</b>	<b>Max</b>	<b>Recommended</b>
<b>Wet Film Per Coat (microns)</b>	155	188	155
<b>Dry Film Per Coat (microns)</b>	75	90	75
<b>Recoat Time (min)</b>	5 Hours	Indefinite	
<b>Theoretical Spread Rate (m<sup>2</sup>/L)</b>	6.4	5.3	6.4

Hardener Details						
Drying characteristics at 75 microns dry film thickness						
<b>Temperature</b>	<b>Touch</b>	<b>Handle</b>	<b>Full Cure</b>	<b>Recoat Min</b>	<b>Recoat Max</b>	
10° C	2 Hours	17 Hours	7 Days	17 Hours	4 Weeks	
15° C	2 Hours	10 Hours	7 Days	10 Hours	4 Weeks	
25° C	1 Hour	5 Hours	7 Days	5 Hours	4 Weeks	
Values are at 50% Relative Humidity						
TYPICAL SPREADING RATE AT RECOMMENDED DRY FILM BUILD			A spreading rate of 6.4 sq. metres per litre corresponds to 75 microns dry film thickness assuming no losses. Practical spreading rates will vary depending on such factors as method and condition of application and surface roughness			
<b>Hardener Section Footer</b>	<p>These figures are given as a guide only, as ventilation, film thickness, humidity, thinning and other factors will influence the rate of drying. To overcoat after the maximum time has elapsed, either with itself or with another product, may require the surface to be abraded in order to ensure adequate adhesion.</p> <p>When used for immersion conditions the maximum overcoat interval is 3 days.</p>					

**Typical Systems**

**Typical System STEEL**

**Preparation Guide** Steel generally: Abrasive blast AS1627.4 Class 2.5  
Steel for immersion service: Abrasive blast to AS1627.4 Class 3.0

Coat	Product	Spread Rate (m <sup>2</sup> /L)	WFT (micron)	DFT (micron)
1st Coat	Zincanode 402	6.4	155	75
2nd Coat	Ferreko No 3	6.0	170	100
3rd Coat	Ferreko No 3	6.0	170	100
<b>Minimum System DFT</b>				275

**Typical System STEEL**

**Preparation Guide** Steel generally: Abrasive blast AS1627.4 Class 2.5

Coat	Product	Spread Rate (m <sup>2</sup> /L)	WFT (micron)	DFT (micron)
1st Coat	Zincanode 402	6.4	155	75
2nd Coat	Duremax GPE - Pc255	5.7	175	125
3rd Coat	Weathermax HBR	7.0	145	100
<b>Minimum System DFT</b>				300

**Notes** Above figures are for standard hardeners and no Weathermax HBR Accelerator.

**Typical System STEEL IN MILD AND INTERIOR ENVIRONMENTS**

**Preparation Guide** Steel generally: Abrasive blast AS1627.4 Class 2.5

Coat	Product	Spread Rate (m <sup>2</sup> /L)	WFT (micron)	DFT (micron)
1st Coat	Zincanode 402	6.4	155	75
2nd Coat	Luxathane R	9.0	110	50
<b>Minimum System DFT</b>				125

**Surface Preparation**

Round off all rough welds, sharp edges and remove weld spatter. Remove grease, oil and other contaminants in accordance with AS1627.1. Rust, millscale, oxide deposits and old paint films on metal surfaces must be removed by abrasive blast cleaning to a minimum of AS1627.4 Class 2.5. Immersed steel must be prepared to AS1627.4 Class 3.

**Application Guide**

<b>Application Method</b>	Stir each can thoroughly until the contents are uniform. Use of a power mixer is recommended. Mix the contents of both packs together thoroughly using a power mixer and allow to stand for 10 minutes. Ensure the clean-up solvent is available before commencing application. Remix thoroughly before using and continue mixing during application.
<b>Brush/Roller</b>	For small areas only. Apply even coats of the mixed material to the prepared surface. Thinning is not normally required, however, up to 50ml/litre of Dulux Epoxy Thinner (920-08925) can be added to ease application. When brushing and rolling additional coats may be required to attain the specified thickness.
<b>Conventional Spray</b>	Thinning is not normally required, however, up to 50ml/litre of Dulux Epoxy Thinner (920-08925) can be added to ease application. Ensure paint is regularly agitated during application to prevent separation. Typical Set-up Graco Air Pro: 1.8mm (239543) Pressure at Triton 308: 70-105 kPa (10-15 p.s.i.) Pressure at Gun: 380-415 kPa (55-60 p.s.i.)
<b>Airless Spray</b>	Standard airless spray equipment such as a Graco Xtreme 45:1 with a fluid tip of 15-17 thou (0.38-0.43mm) and an air supply capable of delivering 550-690 kPa (80-100 p.s.i.) at the pump. Ensure paint is regularly agitated during application to prevent settling. Thinning is not normally required but up to 50 ml/litre of Dulux® Epoxy Thinner (920-08925) may be added to aid application
<b>Precautions</b>	This is an industrial product designed for use by experienced Protective Coating applicators. Where conditions may require variation from the recommendations on this Product Data Sheet contact your nearest Dulux Representative for advice prior to painting. Do not apply in conditions outside the parameters stated in this document without the express written consent of Dulux Australia. Freshly mixed material must not be added to material that has been mixed for some time. The rate of cure is dependent upon temperature. Do not apply at temperatures below 10°C. Do not apply at relative humidity above 85% or when the surface is less than 3°C above the dewpoint. When used for immersion conditions the maximum overcoat interval is 3 days at 25°C. The coating MUST be fully cured and solvent free prior to being placed under immersion conditions. For best results in water immersion conditions replace Dulux Epoxy Thinner (920-08925) with CR Reducer (965-63020). Topcoats of a saponifiable nature such as alkyds must never be applied directly to ZINCANODE402.
<b>Clean Up</b>	Clean all equipment with Dulux Epoxy Thinner (920-08925) immediately after use.

<b>Overcoating</b>
Degrease with Gamlen CA 1 according to the data sheet. Test adhesion of existing coating by standard cross hatch adhesion test. If the coating fails, remove it. High-pressure water wash at 8.3 to 10.3 MPa (1,200-1,500 p.s.i.) to remove chalk and dust. Abrade surface to provide a good key for the new coating. Epoxies must be abraded if recoated outside the recoat window.

<b>Health And Safety</b>	
<b>Safety Precautions</b>	Read Data Sheet, Material Safety Data Sheet and any precautionary labels on containers. Contents of container may be under pressure. Containers should be carefully opened by first placing a rag, then a hand, over the lid then gently easing the lid off.
<b>Storage</b>	Store as required for a flammable liquid Class 3 in a bunded area under cover. Store in well-ventilated area away from sources of heat or ignition. Keep containers closed at all times.
<b>Handling</b>	As with any chemical, ingestion, inhalation and prolonged or repeated skin contact should be avoided by good occupational work practice. Eye protection approved to AS1337 should be worn where there is a risk of splashes entering the eyes. Always wash hands before smoking, eating, drinking or using the toilet.
<b>Using</b>	Use with good ventilation and avoid inhalation of spray mists and fumes. If risk of inhalation of spray mists exists, wear combined organic vapour/particulate respirator. When spray painting, users should comply with the provisions of the respective State Spray Painting Regulations.
<b>Flammability</b>	This product is flammable. All sources of ignition must be eliminated in, or near the working area. DO NOT SMOKE. Fight fire with foam, CO2 or dry chemical powder. On burning will emit toxic fumes.
<b>Welding</b>	Avoid inhalation of fumes if welding surfaces coated with this paint. Grind off coating before welding.
<b>Safety Data Sheet</b>	MATERIAL SAFETY DATA SHEET is available from Customer Service (132377) or <a href="http://www.duluxprotectivecoatings.com.au">www.duluxprotectivecoatings.com.au</a>
<b>In the case of emergency, please call 1800 033 111</b>	

<b>Transport And Storage</b>			
<b>Packaging</b>	Available in 4 litre and 10 litre packs	<b>Transportation</b>	2.12 kg/litre (Average of components)
Dangerous Goods Part A			
<b>Class</b>	3	<b>UN Number</b>	1263
Dangerous Goods Part B			
<b>Class</b>	3	<b>UN Number</b>	1263

**Disclaimer**  
Dulux, Selleys and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating/product systems.  
DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (Australia) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating/product systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Selleys" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "Acratex" and Other marks followed by ® are registered trademarks of DuluxGroup (Australia) Pty Ltd ABN 67 000 049 427. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.  
DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton, Victoria 3168 AU ABN 67 000 049 427