

FEAST WATSON Thru Cure Catalyst

PRODUCT CODE 703 94742

Data Sheet No. AUDW0713

APPROVALS AS2311

Description

Feast Watson Thru Cure Catalyst is used to adjust the cure rate of compatible* moisture cured top coats finish coats at low temperature, or where there is a requirement to achieve quicker cure under normal conditions. Add in the 2 - 5% range.

*Refer to www.duspec.com.au for compatible moisture cured products

Features

Benefits

Uses

Performance Guide

Typical Properties and Application Data

Gloss Level	0	Spread Rate	0.0 sqm/L
Components	1	Colour	Clear
Toxicity	Lead free. Dry film is non-toxic and conforms to AS1647 part 3	Wet film per coat	Recommended 0 µm
Clean Up	Feast Watson Super Solvent	Dry film per coat	Recommended 0 µm



Application Method



Application Guide

Surface Preparation

APPLICATION

Add up to 5% Feast Watson Thru Cure Catalyst into compatible* moisture-cured polyurethanes.

Notes

Feast Watson Thru Cure Catalyst is compatible with:

- Feast Watson Maxithane
- Feast Watson PolyU
- Feast Watson Quickstep
- Toby Unithane

DO NOT USE THRU CURE CATALYST IN THE TOPCOAT, WHEN TOBY GF BARRIER SEAL WAS USED AS THE SEALER.

- Toby Supreme Gloss

Data Sheet	FEAST WATSON Thru Cure Catalyst		
DuSpec Data Code	AUDW0713	Page No	1 of 3
Issue No	8.0	Date Issued	14/12/2011

FEAST WATSON Thru Cure Catalyst

Data Sheet No. AUDW0713

Health and Safety

MSDS Number 10714

Using Safety Precautions Avoid contact with skin and eyes and breathing in vapour or spray mist. Wear overalls, impervious gloves and chemical goggles. Use only in well ventilated areas. If inhalation risk exists wear organic vapour/particulate respirator. Keep away from sources of ignition - No smoking. Take precautionary measures against static discharges. Do not empty into drains. Keep containers closed when not in use.

Health Effects Irritating to eyes and skin.

Flammability This product is flammable

FIRST AID

For advice, contact a Poisons Information Centre (Phone eg. Australia 131 126; New Zealand 0 800 764766) or a doctor.

SWALLOWED: If swallowed, do NOT induce vomiting. Give a glass of water. Seek medical assistance.

EYE: If in eyes, hold eyelids apart and flush the eye continuously with running water. Continue flushing until advised to stop by the Poisons Information Centre or a doctor, or for at least 15 minutes.

SKIN: If skin contact occurs, remove contaminated clothing and wash skin thoroughly.

Protective Equipment Wear overalls, impervious gloves and chemical goggles.

Storage Keep out of reach of children.

Disposal Do not empty into drains. Refer to Waste Management Authority. Dispose of material through a licensed waste contractor.

In the case of emergency please call 1800 033 111

Precautions and Limitations

Use below 10°C is not advised.

It is not advised to apply coatings when the temperature exceeds 35°C as they may dry too quickly under the roller, resulting in a substandard finish.

The drying time will vary greatly when the temperature is below 10°C or above 30°C or if the relative humidity is higher than 50%. Do not exceed the maximum addition of 5%.

Excessive amounts can cause poor intercoat adhesion by over-curing, and gassing in humid conditions and/or high builds

Transport and Storage

Pack A 703 94742

Sizes 4 Litre

Flash point 43C

Weight 4 Kg

UN Number 1263

Dangerous Goods Class 3

Package Group III

Shipment Name PAINTS,

Data Sheet	FEAST WATSON Thru Cure Catalyst		
DuSpec Data Code	AUDW0713	Page No	2 of 3
Issue No	8.0	Date Issued	14/12/2011



DATA SHEET



FEAST WATSON Thru Cure Catalyst	
	Data Sheet No. AUDW0713

Disclaimer

Dulux and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating systems.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (Australia) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "Acratex" and Other marks followed by ® are registered trademarks of DuluxGroup (Australia) Pty Ltd ABN 67 000 049 427. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton, Victoria 3168 AU ABN 67 000 049 427

Data Sheet	FEAST WATSON Thru Cure Catalyst		
DuSpec Data Code	AUDW0713	Page No	3 of 3
Issue No	8.0	Date Issued	14/12/2011