

Dulux Weathershield Roof & Trim Semi Gloss

AUDD0056

Part A	594-LINE
---------------	----------

Description
DULUX Weathershield Roof & Trim is a high opacity, high performance, 100% acrylic paint designed for all types of roofs such as galvanised iron, Colorbond & concrete tiles, and trims such as plastic spouting, timber fascias, masonry & structural metals.






Features
<ul style="list-style-type: none"> • Water based • 100% acrylic paint • Non foaming formulation • Factory packaged colours

Benefits
<ul style="list-style-type: none"> • Same day recoat and easy clean up • Proven excellent durability maximises time before repaint • Suitable for roofs used to collect drinking water • Durable, colourfast colours which will look good for longer

Uses
DULUX Weathershield Roof & Trim is recommended for all types of roofs and structural metals and can also be used on timber fascias. The colours and sheen level closely match BHP Colorbond® prepainted steel, allowing colour co-ordination of trim items. This product is suitable for roofs used to collect drinking water. Dulux guarantees that Weathershield Roof & Trim will not blister, flake or peel for 10 years on metal roofs, timber and masonry, provided it is applied on properly prepared surfaces as per the label directions. This guarantee does not cover paint failure caused by any breakdown of coatings applied previously or when used on concrete tiles and plastics.

Precautions And Limitations
<p>All preparation and painting must conform to AS 2311: The Painting of Buildings. Do not apply at temperatures below 10C or when the temperature may fall below 10C during the drying period. In hot and windy conditions, paint on the shady side of the building, or cool the surface by hosing and paint the cool damp surface. Rain, frost or dew during the drying period will damage the film.</p> <p>Check the suitability of DULUX Weathershield Roof over previously painted surfaces by cleaning the surface, painting a small section then leaving to dry for two days. Cut an 'X' through the coating with a sharp blade. Press cellulose tape firmly across the cut and then rip the tape off. If DULUX Weathershield Roof is removed from the previous paint, the surface is not suitable for painting.</p> <p>Do not collect drinking water within 48 hours after painting to allow coating to fully dry.</p>

Performance Guide			
Weather	Excellent resistance to weathering, with very low level of chalking and colour change.	Heat Resistance	Softens and suffers from dirt pick up above 70C.
Water	Resists prolonged rain and condensation.	Solvent	Sensitive to aromatic hydrocarbons, alcohols and ketones.
Abrasion	Good resistance to abrasion.		

Typical Properties																											
Gloss Level	20-30 at 60 degrees	Thinner	Water																								
Colour	A range of the most popular BHP Colorbond® prepainted steel colours.	Components	1																								
Number Of Coats	2	Toxicity	Lead free. Dry film is non-toxic.																								
V.O.C. Level	< 95g/L untinted	Touch Dry	20 Minutes																								
Clean Up	 Water																										
Clean Up Description	Clean all equipment with water																										
Application Method	    Air Spray Airless Spray Brush Roller																										
Application Conditions	<table border="0" style="width: 100%;"> <tr> <td style="text-align: center;">Solids By Volume</td> <td style="text-align: center;">40</td> <td></td> <td></td> </tr> <tr> <td></td> <td style="text-align: center;">Min</td> <td style="text-align: center;">Max</td> <td style="text-align: center;">Recommended</td> </tr> <tr> <td>Wet Film Per Coat (microns)</td> <td style="text-align: center;">62</td> <td style="text-align: center;">62</td> <td style="text-align: center;">62</td> </tr> <tr> <td>Dry Film Per Coat (microns)</td> <td style="text-align: center;">25</td> <td style="text-align: center;">25</td> <td style="text-align: center;">25</td> </tr> <tr> <td>Recoat Time (min)</td> <td style="text-align: center;">2 Hours</td> <td style="text-align: center;">Indefinite</td> <td></td> </tr> <tr> <td>Theoretical Spread Rate (m²/L)</td> <td style="text-align: center;">16</td> <td style="text-align: center;">16</td> <td style="text-align: center;">16</td> </tr> </table>			Solids By Volume	40				Min	Max	Recommended	Wet Film Per Coat (microns)	62	62	62	Dry Film Per Coat (microns)	25	25	25	Recoat Time (min)	2 Hours	Indefinite		Theoretical Spread Rate (m²/L)	16	16	16
Solids By Volume	40																										
	Min	Max	Recommended																								
Wet Film Per Coat (microns)	62	62	62																								
Dry Film Per Coat (microns)	25	25	25																								
Recoat Time (min)	2 Hours	Indefinite																									
Theoretical Spread Rate (m²/L)	16	16	16																								

Application Guide	
Surface Preparation	<ul style="list-style-type: none"> All surfaces must be thoroughly cleaned and free of all dirt, loose and flaking paint. In checking the suitability of a previously painted surface for recoating with Weathershield Roof & Trim, use the test described below. If all the paint layers are removed by the cellulose tape, the original coating needs to be removed before painting. Bare Galvanised Iron: Remove dirt and roll forming oils by washing with a detergent solution such as Sugar Soap. Rinse using high pressure water, allow to dry and prime with DULUX Galvanised Iron Primer. Colorbond: Rinse using high pressure water, allow to dry before applying Weathershield Roof directly to substrate. For improved adhesion very light sanding is recommended. Concrete Tiles: Remove all dirt, chalk, lichens, moss and mould. To avoid dust, do not sand asbestos cement sheet. Wash with a bleach solution and de-mossing chemical where necessary. Hose down only. Ensure that all pointing is sound. Apply one coat of Dulux AcraTex Roof Sealer WB for tile in good condition or Roof Sealer SB for heavily weathered tiles. Ensure to follow label directions and Contact Dulux Customer Service on 13 25 25 for further advice.
Application Procedure And Equipment	<ul style="list-style-type: none"> Brush, roller, conventional or airless spray Stir well before use with a broad flat paddle, using an up and down scooping action. Two coats are normally required to give the desired finish but this will depend upon application technique and the condition of the substrate. Brush/Roller: Rinse brush or roller in water before starting and use while still slightly damp. Changeover brushes at half hourly intervals and rinse to remove paint build up. To ease application in hot conditions, add up to 100ml of DULUX Hot Weather Thinner per litre. Airless/Conventional Spray: Suitable for spray by all standard spray equipment. If necessary thin with up to 100ml of water per litre to aid atomisation. <p style="text-align: center;">COLORBOND® IS A REGISTERED TRADE MARK OF THE BHP GROUP OF COMPANIES.</p>

Health And Safety			
MSDS Number	10745, 0	Health Effects	For detailed information refer to the product label and the current Material Safety Data Sheet available through Customer Service. Splashes to the eye may cause eye irritation. When spraying, inhalation of mists may produce respiratory irritation.
Protective Equipment	Wear eye protection and when spraying wear a dust mask.		
In the case of emergency, please call 1800 033 111			

Transport And Storage			
Pack A	594-LINE	Shipment Name	Not dangerous goods.; No special transport requirements.
Size 4 Litre 10 Litre	Weight 5.7 Kg 14.1 Kg		
Flash Point	NA	UN Number	NA
Dangerous Goods Class	NA	Package Group	NA

Disclaimer

Dulux, Selleys and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating/product systems.
 DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (Australia) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating/product systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Selleys" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "Acratex" and Other marks followed by ® are registered trademarks of DuluxGroup (Australia) Pty Ltd ABN 67 000 049 427. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton, Victoria 3168 AU ABN 67 000 049 427