

Dulux Powder Coatings Electro®

AU_DP01900

Product Code	906 Line
Approval	Architectural Aluminium Standards: Meets or exceeds AS3715, AAMA2604 Classification of fire performance for Electro has a Group Classification of 1 according to the National Construction Code (NCC) Volume One Specifications C1.10 clause 4 of the Building Code of Australia (BCA).

Description

Electro® are a range of unique anodised look finishes, designed to subtly change in appearance as light conditions alter in the day, delivered with warranty grade advanced super durable polyester thermosetting powder.

Ideal for warranty grade applications over:

- Architectural aluminium including perforated and expanded aluminium
- Steel (mild), bright/semi bright steel, black steel and blue steel

Electro® can also be used on the following metals but these are not warranted:

- Galvanised steel, stainless steel, zincalume and non ferrous metals

Electro® is supported by Alumi Shield™ and Steel Shield™ warranties* when applied by a Dulux Accredited Powder Coater to the warranty specification on recommended project types and conditions.

*Subject to the terms and conditions of the relevant product warranty. Please contact your local Dulux representative for further details.

IMPORTANT INFORMATION - CARE & MAINTENANCE POST INSTALLATION

A SIMPLE AND REGULAR MAINTENANCE PROGRAM MUST BE IMPLEMENTED AND RECORDED IN LINE WITH THE DULUX POWDERS CARE AND MAINTENANCE SCHEDULE TO:

1. Comply with Dulux Warranty Requirements
2. Ensure the life of your asset is maximised

It is important that architects, specifiers, powder coaters, fabricators, manufactures and builders ensure they reinforce this message to the end asset owner.

For more information refer to the Dulux Care and Maintenance brochure available at duluxpowders.com.au/tech-advice or call 13 24 99

Features And Benefits

- | | |
|---|--|
| <ul style="list-style-type: none"> • Super Durable Polyester Thermosetting Powder • Alumi Shield™ warranty 25 Year Aluminium Durability and 15 Year Aluminium Colour Warranty • Steel Shield™ warranty - Up to 10 Year Steel Corrosion Warranty and 15 Year Steel Colour Warranty • Alternative colour range to anodising • No solvents or emissions & TGIC free • Formulated to meet: AS 3715, AAMA 2603 and AAMA 2604 | <ul style="list-style-type: none"> • Guaranteed performance on appropriately pre-treated aluminium and steel* • Excellent colour retention • Super durable finish • Ideal for use on environments greater than 10m from the high tide mark • On trend anodised flat finish • Less waste and pollution to the environment & reduced risk to health • Good flow out |
|---|--|

Uses

Electro® has been developed as an alternative to anodised finishes for use on a wide range of metal substrates including, most architectural aluminium applications such as window and door system, louvres, balustrades, sunshades, perforated screen, curtain walls, shop fronts, furniture and shelving.

It is ideal for:

Exterior projects (All BCA Classes)

- All commercial buildings
- All residential buildings
- Non-habitable

Interior projects (All BCA Classes):

- All commercial buildings
- All residential buildings
- Non-habitable

Precautions And Limitations

Electro® is only available in solid and pearl colours which meet Dulux Powder Coatings pigmentation criteria. Strong, bold colours may not necessarily meet these criteria and should be referred to Dulux Powder Coatings before specifying.

As a result of possible wide application variations and stoving conditions, some products and colours may show variation between Dulux Powder Coatings prepared samples and production applied material. Therefore, it is the applicator and/or their customer's responsibility to ensure the product conforms to their requirements.

For optimum performance ensure recommended dry film thickness is obtained. Some light colours require increased film thickness average to achieve optimal consistency.

Not recommended for use in highly corrosive environments such as severe marine or industrial locations.

Not recommended for components which are exposed to constant temperatures exceeding 120°C.

Not recommended for post-forming.

Performance Guide			
Exterior Durability	Excellent resistance to weathering, providing extended protection for aluminium	Salt	Excellent salt spray resistance over pre-treated aluminium. (3000 hours ASTM B117)
Heat Resistance	Excellent resistance to 120°C continuous service conditions	Water	Excellent resistance to 38°C/100% humidity for 3000 hours on pre-treated aluminium
Solvent	Resistant to alcohol and white spirits.	Abrasion	Abrasion Excellent resistance to abrasion. Abrasion Coefficient > 20 (ASTM D968)
Acid	Resistant to spills of dilute acid. Avoid contact	Alkali	Resistant to spills of dilute alkali. Avoid contact

Typical Properties			
Gloss Level	Less than 10 at 60° (Black Ace) 5 -15 at 60° (Dark Bronze, Brilliance, Blueit, Basalt, Monument) 10 -20 at 60° (Fresh Gold, Poyle, Blue Gold, Green Lantern, Blue Night, Burnished Copper, Flat White, Venerable Silver, Sensational Champagne, Silver Reign, Clean Linen, Canary, Medium Bronze, Tiberius) 15 -25 at 60° (Bright Spark) 20 -30 at 60° (Fred)	Coverage	8 - 10m2/kg corresponds to 80um cured film thickness
Shelf Life	At least 2 years from date of manufacture if stored at < 25 °C.	V.O.C Level	Nil
Colour	A limited range of stock and made to order solid & pearl colours		
Meets GBCA VOC Requirement?	Yes. Dulux Powder Coatings: <ul style="list-style-type: none"> ▪ Contain no harmful volatile organic solvents ▪ Free of heavy metal pigments such as lead, cadmium, arsenic & mercury ▪ Proven low temperature curing technology ▪ Produced with stringent Safety, Health & Environmental policies and standards ▪ Developed with consideration of life cycle analysis, to guide our suppliers and the materials we use ▪ Manufactured in facilities where significant energy and resources employed in production, are measured with aggressive reduction targets in place ▪ Produced and used with minimal waste Consequently, Dulux ® Powder Coatings are a prime consideration for projects where air quality standards have been set, such as 4, 5 & 6 Green Star Rating Projects.		
Film Build (microns)	Recommended 80um, range 60-120µm (NB Flat White: 90 - 120µm)	Clean Up	Dust or vacuum loose powder. Avoid use of compressed air
Application Method	Electrostatic Spray. Recommended 70KV.	Specific Gravity	1.3 - 1.7
Flexibility	Limited < or = 80 inch/lb	Pencil Hardness	Min H
Cross Hatch Adhesion	No removal	Chemical Resistance	Mortar Resistant White Spirits Resistant Ethanol Resistant Xylene Methyl Slight softening/limit contact Ethyl Ketone Softens/avoid contact Ethyl Acetate Softens/avoid contact
Cure Schedule	Metal Temperature (°C) 200 210	Time (minutes) 10 Mins 8 Mins	Comments Metal temperature Metal temperature

Application Guide

Surface Preparation	<ul style="list-style-type: none"> Surfaces should be prepared according to AS1627.6-2003 Section 3 to achieve a conversion coating corresponding to Class 1. chemical supplier recommendations should also be adhered to, as appropriate. Suitable pre-treatment includes: Aluminium - Chrome chromate (refer AS1627.6-2003 Section 3)
Application Procedure And Equipment	<ul style="list-style-type: none"> Electrostatic spray. Light colours may require a higher minimum film build for optimum coverage and colour consistency. Theoretical spreading rate at recommended film thickness: A coverage rate of 8 - 10m²/kg corresponds to 80 microns cured film thickness assuming no loss. Practical spreading rates will vary due to such factors as method and conditions of application and surface profile and texture. Applied by Dulux Accredited Powder Coater with equipment and control systems to enable correct metal pre-treatment and control of the application and stoving as set out in the Applicators Manual. 1a) For fluidised bed, ensure uniform fluidisation of powder. Fluidised powder should resemble "simmering liquid". Aged or compacted powder may require pre-conditioning for several minutes to fluidise evenly. 1b) For box feeders, ensure probe is fully inserted in powder and operated as per manufacturer's recommendations. Box feeders are not suitable for the application of pearlescent & metallic finishes. 2 Apply by electrostatic spray. 3 Cure as per recommendations outlined above. Metal temperatures in excess of 210°C should be avoided due to the possibility of colour change or thermal degradation of the polymer. 4 Test for cure of the coating by contact with a drop of Corsol PGMA for 30 seconds. Surface should be wiped dry and immediately checked for softening. Only slight surface softening should occur.

Care And Maintenance

PACKAGING PRE INSTALLATION
Attention to packing is essential for powder coaters and fabricators to ensure that all powder coated sections are received in good condition. When packing powder coated assets, it is recommended that:

- Sections must be adequately cooled prior to packing; the metal temperature must not exceed 40°C on packing.
- Appropriate protective wrapping is recommended prior to packing to avoid damage during transport.
- If protective tapes are used, ensure that the tape will remain removable following transport, fabrication and installation and not irreversibly mark or damage the coating. Tapes should be used in accordance with the manufacturer's instructions and only remain in contact for the minimum amount of time.
- Packed metal should be kept away from sunlight or moisture to avoid coating defects.

CARE & MAINTENANCE POST INSTALLATION
A SIMPLE AND REGULAR MAINTENANCE PROGRAM MUST BE IMPLEMENTED AND RECORDED IN LINE WITH THE DULUX POWDERS CARE AND MAINTENANCE SCHEDULE TO:

1. Comply with Dulux Warranty Requirements
2. Ensure the life of your asset is maximised

It is important that architects, specifiers, powder coaters, fabricators, manufactures and builders ensure they reinforce this message to the end asset owner.
For more information refer to the Dulux Care and Maintenance brochure available at duluxpowders.com.au/tech-advice or call 13 24 99

Health And Safety

MSDS Number	00000022803	Safety Precautions	<p>Safety Precautions The MSDS is an integral part of using this product as it contains information on the potential health effect of exposure, personal protective equipment needed and other relevant SH&E information.</p> <p>For detailed information, refer to product label and the current Chemical Data Sheet available through Sales and Customer Service Offices.</p> <p>Phone: Australia: 13 24 99</p>
--------------------	-------------	---------------------------	---

In the case of emergency, please call 1800 033 111

Transport And Storage

Package Weight	20 Kg	Shipment Name	Not dangerous goods. No special transport requirements
Flash Point	N/A	UN Number	N/A
Dangerous Goods Class	N/A	Package Group	N/A

Images



For more information visit duluxpowders.com.au/accredited

Disclaimer

Dulux, Selleys and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating/product systems.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (Australia) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating/product systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Selleys" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "Acratex" and Other marks followed by ® are registered trademarks of DuluxGroup (Australia) Pty Ltd ABN 67 000 049 427. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton, Victoria 3168 AU ABN 67 000 049 427